

**SYDNEY**

25 – 27 Green St  
East Botany, NSW 2019  
Ph: +61 2 9666 3788  
Fax: +61 2 9666 4805

**MELBOURNE**

29 Trade Place  
Vermont, VIC 3133  
Ph: 03 9872 4033  
Fax: 03 9872 4099

**BRISBANE**

Unit 6/5 Deakin Street  
Brendale, QLD 4500  
Ph: 07 3205 8510  
Fax: 07 3205 9616

**SINGAPORE**

H.K. Moey  
9 Elias Terrace  
Singapore 519772  
Ph: +65 6582 8103  
Fax: +65 6584 8100  
Mobile: +65 9751 0026



# TECHNICAL DATA

## Erelease W

### MOULD CONDITIONING WAX

**Erelease W** is a paste product extensively used in the conditioning of moulds prior to mould release application. Its hard dry film is an excellent base for any conventional solvent borne release agents on all mould surfaces.

## PRODUCT SPECIFICATION

<b>Colour</b>	White to off-white paste
<b>Specific gravity</b>	0.79
<b>Flashpoint</b>	Minimum 39°C

## APPLICATION DETAILS

We recommend application by soft, non-abrasive cloth.

Apply to total mould surface.

Rub into cracks, crevices, etc. and wipe off excess.

Allow 5-10 minutes to harden before applying **Erelease** release agent by normal means.

Dilute with alcohols such as methanol (methylated spirits) and isopropyl alcohol (IPA) for easier application.

**CAUTION:** Use in well ventilated areas. Avoid breathing vapours or fumes. Avoid contact with skin and eyes. If contact occurs, wash immediately with soap and water.

## STORAGE

Should be stored at less than 38°C. Container should be tightly sealed to prevent evaporation and drying.

This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

