

**SYDNEY**

25 – 27 Green St  
East Botany, NSW 2019  
Ph: +61 2 9666 3788  
Fax: +61 2 9666 4805

**MELBOURNE**

29 Trade Place  
Vermont, VIC 3133  
Ph: 03 9872 4033  
Fax: 03 9872 4099

**BRISBANE**

Unit 6/5 Deakin Street  
Brendale, QLD 4500  
Ph: 07 3205 8510  
Fax: 07 3205 9616

**SINGAPORE**

H.K. Moey  
9 Elias Terrace  
Singapore 519772  
Ph: +65 6582 8103  
Fax: +65 6584 8100  
Mobile: +65 9751 0026

**Salease Classic** is a low viscosity liquid mould release agent based on heavy-duty silicones. It gives excellent release characteristics for simple and complex potting, casting and moulding operations.

**APPLICATION**

**SALEASE CLASSIC** releases polyurethane, epoxy, polyester and most other polymers, regardless of catalysts and fillers, from metals, polymers and any other non-porous moulds. It works equally well at room temperature and at elevated processing temperatures. **Salease Classic** leaves a thin film of silicone thus allowing reproduction of the finest detail.

**PRODUCT SPECIFICATION**

<b>Colour</b>	Clear
<b>Specific gravity at 20°C (g/cm<sup>3</sup>)</b>	0.73
<b>Flashpoint</b>	-4°C

**APPLICATION DETAILS**

Apply **SALEASE CLASSIC** to clean moulds by dipping, brushing or spraying. Drain excess release agent from the mould and air-dry between 5 and 10 minutes (less at elevated temperatures).

For optimum surface results, lightly buff the inside of the mould with a clean, lint-free cloth after drying. It is not necessary to reapply **SALEASE CLASSIC** after each demould cycle.

Periodically clean moulds to remove any dirt or build-up with a suitable solvent depending on mould material.

**CAUTION:** Read the product's MSDS before use. This product contains flammable solvent. All appropriate precautions must be taken when using flammable liquids.

Use in well ventilated areas. Avoid inhaling vapours or fumes. Avoid contact with skin and eyes. If contact occurs, wash immediately with soap and water.



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.