



Era Polymers Pty. Ltd.
 2-4 Green Street, Banksmeadow
 Sydney, NSW 2019
 AUSTRALIA
 www.erapol.com.au

Erapol XLE90A

POLYETHER (PTMEG) TDI PREPOLYMER –
 LOW FREE TDI CONTENT

TECHNICAL DATASHEET

Erapol XLE90A is a new generation of liquid isocyanate terminated prepolymer based on 100% PTMEG polyether polyol with the added benefit of extremely low free isocyanate.

Polymers made from **Erapol XLE90A** exhibit outstanding abrasion, impact and chemical resistance, along with high load bearing capacity and low heat build-up in dynamic applications.

Additionally, **Erapol XLE90A** has a low free TDI content (less than 0.1%) - low viscosity and long pot life make processing easy.

Application

Typical uses of this polymer include forklift truck tyres, roles and gears, die pads etc.

Product Specification

% NCO	4.50 ± 0.20
Specific Gravity at 30°C (g/cm³)	1.03
Viscosity at 80°C (cps)	400 - 700
Colour	Clear, light amber

Mixing and Curing Conditions

		XLE90A / MOCA	XLE90A / Ethacure 300	XLE90A / Eracure 110
Erapol XLE90A	(pph)	100	100	100
MOCA Level	(pph)	13.6	-	-
Ethacure 300 Level	(pph)	-	10.9	-
Eracure 110 Level	(pph)	-	-	11.6
Recommended % Theory		95	95	95
Erapol Temperature	(°C)	75 - 85	75 - 80	75 - 80
Curative Temperature	(°C)	110 - 120	20 - 30	20 - 30
Pot Life	(mins)	14	8	8
Demould Time at 100°C	(mins)	30	20	20
Post Cure Time at 100°C	(hrs)	16	16	16



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

Physical Properties

Properties presented below are to be used as a guide and not intended for specification purposes.

		XLE90A / MOCA	XLE90A / E300*	XLE90A / E110**	TEST METHOD
Hardness	(Shore A)	90 ± 3	90 ± 3	90 ± 3	AS1683.15
Tensile Strength	MPa (psi)	33.6 (4873)	33.2 (4815)	31.5 (4569)	AS1683.11
100% Modulus	MPa (psi)	8.5 (1233)	8.5 (1233)	8.2 (1189)	AS1683.11
200% Modulus	MPa (psi)	12.6 (1827)	11.9 (1726)	11.0 (1595)	AS1683.11
300% Modulus	MPa (psi)	19.8 (2872)	17.2 (2495)	15.5 (2248)	AS1683.11
Elongation	(%)	425	480	478	AS1683.11
Angle Tear Strength, Die C	kN/m (pli)	78.8 (450)	84.3 (481)	81.1 (463)	AS1683.12
Trouser Tear Strength	kN/m (pli)	25.5 (146)	22.6 (129)	19.6 (112)	AS1683.12
DIN Resilience	(%)	53	55	56	DIN 53512
DIN Abrasion Resistance 10N	(mm ³)	53	65	43	AS1683.21
Compression Set / 22 hr at 70°C	(%)	20	34	34	AS1683.13
Cured Specific Gravity	(g/cm ³)	1.09	1.08	1.08	AS1683.4

*Ethacure 300 **Eracure 110

Processing Procedure

1. **Erapol XLE90A** should be heated to 80 ± 5°C and thoroughly degassed at -95 kpa of vacuum until excessive foaming stops.
2. The curative should be added to **XLE90A**, the MOCA must first be melted at 110 – 120°C and Ethacure 300 and Eracure 110 processed at room temperature. After adding the curative, mix thoroughly being careful not to introduce air into the mixture.
3. Pour mixed materials into moulds, which have been preheated to 100°C and pre-coated with release agent.

Adhesion

Adhesion of Erapol based elastomers to various substrates it at best marginal if a primer is not used. Please consult Era Polymers for specific recommendations to improve adhesion.

Handling Precautions

Erapol XLE90A contains small amounts of free TDI. Therefore the product should be used in well-ventilated areas. Avoid breathing in vapours and protect skin and eyes from contact.

In case of skin contact, immediately remove excess, wash with soap and water. For eye contact, immediately flush with water for at least 15 minutes. Call a physician.

If nose, throat or lungs become irritated from breathing in vapours, remove exposed person to fresh air. Call a physician.



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.