

SYDNEY

25 – 27 Green St
East Botany, NSW 2019
Ph: +61 2 9666 3788
Fax: +61 2 9666 4805

MELBOURNE

29 Trade Place
Vermont, VIC 3133
Ph: 03 9872 4033
Fax: 03 9872 4099

BRISBANE

Unit 6/5 Deakin Street
Brendale, QLD 4500
Ph: 07 3205 8510
Fax: 07 3205 9616

SINGAPORE

H.K. Moey
9 Elias Terrace
Singapore 519772
Ph: +65 6582 8103
Fax: +65 6584 8100
Mobile: +65 9751 0026



TECHNICAL DATA

Ecofoam GP280

RIGID POLYURETHANE APPLIANCE FOAM

Ecofoam GP280 is a rigid polyurethane foam product for pour in place applications, with a free rise density of 28 kg/m³. This product contains no CFC's or HCFC's blowing agents.

The product can be hand-mixed or processed through a polyurethane foam dispensing equipment..

COMPONENT PROPERTIES

| | Polyol | Isocyanate |
|-----------------------------------|------------------------------|-------------------|
| Appearance | Clear, Amber coloured liquid | Brown liquid |
| Brookfield Viscosity (cps) | 680 | 250 |
| Specific Gravity | 1.13 | 1.22 |

REACTION PROFILE

Laboratory results based on hand-mix @ 20°C

Mix ratio by weight (Polyol: Iso) 100:113
Mix ratio by volume (Polyol: Iso) 1:1

| | |
|---|-----|
| Mix time (seconds) | 8 |
| Cream time (seconds) | 16 |
| Gel time (seconds) | 105 |
| Tack free time (seconds) | 220 |
| Free rise densities (kg/m³) | 28 |

This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.



Era Polymers Pty. Ltd.

A.B.N. 14 003 055 936

erapol@erapol.com.au
www.erapol.com.au

SYDNEY

25 – 27 Green St
East Botany, NSW 2019
Ph: +61 2 9666 3788
Fax: +61 2 9666 4805

MELBOURNE

29 Trade Place
Vermont, VIC 3133
Ph: 03 9872 4033
Fax: 03 9872 4099

BRISBANE

Unit 6/5 Deakin Street
Brendale, QLD 4500
Ph: 07 3205 8510
Fax: 07 3205 9616

SINGAPORE

H.K. Moey
9 Elias Terrace
Singapore 519772
Ph: +65 6582 8103
Fax: +65 6584 8100
Mobile: +65 9751 0026

STORAGE CONDITIONS AND HANDLING

The components are sensitive to humidity and should at all times be stored in sealed drums. The recommended storage temperatures are 18-25°C, which will give a normal shelf life of 3 months. At elevated temperatures problems may arise with pressure build-up within the drums. When opening these drums extreme care must be exercised in releasing the internal pressure. It is recommended that the drum contents should be mixed well before use.

HEALTH AND PERSONAL PROTECTION

Before handling these chemicals please consult the Material Safety Data Sheets for the two components. The polyol component contains tertiary amines. Contact with the skin or eyes must be avoided. Safety goggles and protective gloves should be worn whenever handling both of the chemicals. Splashes that come into contact with the skin must be wiped off immediately and the contaminated area washed with soap and water. Splashes in the eye must be flushed immediately with plenty of clean running water. If irritation occurs thereafter contact an eye specialist.

GENERAL INFORMATION

The degree of insulation is determined by the thickness of the foam.

At temperatures less than 15°C the reaction rate of Ecofoam GP280 will be much slower resulting in an increase in density, and reduction in foam yield and quality. Also at temperatures above 30°C the cream time will be drastically reduced.



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

Version: 2

Date of Issue: 18/8/2008

Page 2 of 2
Ecofoam GP280